

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES


Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 731 128 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
11.09.1996 Bulletin 1996/37

(51) Int Cl.⁶: **C08J 3/12**
// C04B24/26

(21) Application number: **96300936.0**

(22) Date of filing: **12.02.1996**

(84) Designated Contracting States:
BE CH DE ES FR GB IT LI NL SE

(30) Priority: **16.02.1995 US 390389**

(71) Applicant: **ROHM AND HAAS COMPANY**
Philadelphia, Pennsylvania 19106-2399 (US)

(72) Inventors:
• **Chiou, Shang Jaw**
Lower Gwynedd, Pennsylvania 19002 (US)

• **Sheng, Miao-Hsun Li**
Lower Gwynedd, Pennsylvania 19002 (US)

(74) Representative: **Tanner, James Percival et al**
ROHM AND HAAS (UK) LTD.
European Operations Patent Department
Lennig House
2 Mason's Avenue
Croydon CR9 3NB (GB)

(54) **Improved polymer powder stability**

(57) A method for improved polymer powder stability is provided, particularly spray-dried emulsion poly-

mers, by spray-drying emulsion polymers with selected low HLB surfactants. Stable spray-dried emulsion polymers are particularly useful as cement modifiers.

EP 0 731 128 A1

Description.

The present invention relates to improved polymer powder stability. In particular, the present invention relates to improved stability of spray-dried emulsion polymers.

5 Polymers are known to be useful in many physical forms including powders. Several methods are known for preparing powders of polymers. One of the more practical methods for preparing powders of emulsion polymers is by spray-drying a polymer-emulsion. However, spray-drying emulsion polymers has some drawbacks. For example, the yield of powder product may be low.

10 Another drawback to many spray-dried emulsion polymers is the poor storage stability of the spray-dried emulsion polymers. Poor stability may be manifested by clumping of the powder. In certain applications, such as cement modification, it is desirable to have the polymer powder be redispersible in the cement formulation. Poor storage stability may also be indicated by the degradation of performance, as manifested by the lack of redispersibility of the spray-dried emulsion polymer in the cement formulation.

15 One method for attempting to overcome the problems associated with spray-drying redispersible emulsion polymers was to add polyvinyl alcohol to the emulsion prior to spray-drying as taught in European Patent Application Number 0601518A. When polyvinyl alcohol is added to cement modifier emulsion polymers, there is a tendency for phase separation. Also, the addition of polyvinyl alcohol to the emulsion tends to impart poor rheology characteristics of cement compositions containing this mixture.

20 The present invention seeks to overcome the problems associated with known methods for providing redispersible polymer powders.

The present invention provides a method comprising

(i) providing an emulsion comprising at least one emulsion polymer and at least one surfactant having an HLB value below 7 wherein said surfactant is a nonionic surfactant selected from the group consisting of alkylphenoxy ethoxylates, acetylenic polyols, alkylene glycol alkylates, sorbitan alkalates, glycerol esters, polyglycerol esters, and combinations thereof; and

(ii) spray-drying the emulsion.

30 The method of the present invention provides spray-dried polymers having improved storage stability and redispersibility. The method of the present invention also improves the amount of polymer which is recovered during the spray-drying process.

As used herein and in the appended claims, "HLB" refers to hydrophilic/lipophile balance. Surfactants which have a low HLB tend to be less water-soluble and more oil-soluble than surfactants which have a higher HLB.

35 Surfactants suitable for the present invention are nonionic surfactants having HLB below 7, preferably below 6, more preferably below 5. Nonionic surfactants tend to produce less foam than other classes of surfactants. Surfactants useful in the present invention include, for example: alkylphenoxy ethoxylates such as octylphenoxy ethoxylated alcohols; acetylenic polyols such as ethoxylated tetramethyl decynediol; alkylene glycol alkylates such as propylene glycol monolaurate; sorbitan alkalates such as sorbitan monostearate and sorbitan oleate; glycerol esters such as glycerol oleate; polyglycerol esters such as decaglycerol decastearate and decaglycerol decaoleate; and combinations thereof; which have an HLB below 7, preferably below 6, more preferably below 5. Nonionic surfactants such as ethylene oxide/propylene oxide block copolymers, even if the HLB is below 7, do not provide the benefits of the present invention. For example, ethylene oxide/propylene oxide block copolymers tend to result in high levels of caking on the walls of the spray-drying chamber.

45 The surfactants useful in the present invention may be added prior to the polymerization of the emulsion polymers, during the polymerization of the emulsion polymers, after the polymerization of the emulsion polymers or a combination thereof. Preferably, the surfactants useful in the present invention are used as the emulsifier for the emulsion polymerization and are thus added prior to the polymerization of the emulsion polymers. The surfactants useful in the present invention may also be used in combination with one or more conventional surfactants useful in emulsion polymerization. The surfactants useful in the present invention are preferably used at a level of from 0.1 to 20, more preferably from 0.2 to 18, most preferably from 0.5 to 15 percent by weight based on the total weight emulsion polymer.

50 The various aspects of emulsion polymerization are well known to those skilled in the art, such as the selection of the type and amount of monomer(s) and initiator, the selection of the type and amount of chain transfer agents, the control of pH, the rate of addition of the various components, the polymerization temperature, the level of solids, the heating profile, and the like. When preparing emulsion polymers intended for use as cement modifiers, it is preferred that the emulsion polymers are core-shell emulsion polymers, preferably core-shell polymers of the type disclosed in European Patent Application No EP 522791 A1.

55 The various aspects of spray-drying are also well known to those skilled in the art, such as the selection of flow

rates, inlet temperatures, outlet temperature, residence time, the type and amount of additives and type of carrier gas.

Preferably, the emulsion polymers are prepared via an aqueous emulsion process. Preferably, the aqueous emulsion is from 25 to 70 percent by weight polymer solids, more preferably from 30 to 60 percent by weight polymer solids, and most preferably from 35 to 55 percent by weight polymer solids. Preferably, the viscosity of the aqueous emulsion of the present invention is below 5,000 centipoises ("cps"), more preferably from 50 to 2,000 cps to allow for easier handling and pumping the emulsion through the nozzle of the spray drier.

The emulsion polymers prepared by the present invention are useful in the form of an aqueous emulsion and as a spray-dried polymer powder. The use of low HLB surfactants does not present foaming problems when the low HLB surfactant is used as an emulsifier during the emulsion polymerization, the low HLB surfactant improves the yield of product upon spray-drying, and the low HLB surfactant improves the stability of the spray-dried polymer powder.

EXAMPLES

Polymer Synthesis

The following procedure was used to prepare core-shell polymers. The surfactants used in each of the examples are set forth in Table V, below.

To a 5 liter, 4-necked round bottom flask equipped with a mechanical stirrer, thermocouple, condenser, and nitrogen sparge was added 700 grams of deionized water. The water was heated to 80°C. A monomer emulsion (ME#1) was prepared by combining the components set forth in Table I below. An initiator solution was prepared by combining the components set forth in Table II below. While stirring the contents of the kettle, ME#1 was added to the kettle followed by the initiator solution. After several minutes, the temperature of the kettle leveled off, a few grams of a catalyst solution containing t-butylhydroperoxide and sodium sulfoxylate formaldehyde was added to the kettle to reduce the residual monomer level. To the kettle was added the neutralizer slurry (as shown in Table III below) to solubilize the first stage (shell) polymer.

A monomer emulsion (ME#2) was prepared by combining the components set forth in Table IV below. To the kettle was added 114 grams of ME#2 and 10 grams of a 20 percent aqueous solution of ammonium persulfate. After the exotherm peaked, the remainder of ME#2 and 187 grams of a 3.7 percent aqueous solution of ammonium persulfate were separately added to the kettle at a constant rate over a period of two hours at a temperature in the range of 82-86°C. The contents of the kettle temperature were then maintained at 82°C for an additional thirty minutes, then cooled to 65°C. Residual monomer levels were reduced by adding a few grams of a catalyst solution containing t-butylhydroperoxide and sodium sulfoxylate formaldehyde to the kettle.

The emulsion polymers were spray-dried in a Bowen Model BLSA spray dryer under the following conditions: Inlet temperature 120°C; Outlet Temperature 60°C; Flow Rate 100-150 milliliters per minute; Air Pressure 100 pounds per square inch. In each of the examples, "Particle Size" is reported as diameter in nanometers ("nm") as measured by a Brookhaven BI-90 Particle Sizer. The Scrap Ratio reported in Table VII below is the amount of spray dried emulsion polymer, by weight, recovered relative to the amount of polymer which adhered to the walls of the spray drying chamber. The spray-dried emulsion polymers were evaluated as cement modifiers. Cement mortars were prepared according to the formulation set forth in Table VI below.

The following properties of the modified cements were evaluated, and the results are set forth in Table VII below.:

Wet-out time: the time required for the mortar to reach a very workable consistency, reported in seconds ("sec.").

Thin section properties: a 1/16 inch (0.16 centimeter) thickness of mortar is placed on plywood and allow to cure for 24 hours. Toughness is rated qualitatively by scratching the center with a screw driver. Adhesion is rated qualitatively by evaluating how well the cement adhered to the plywood.

"Fresh" polymer refers to spray dried emulsion polymer incorporated into the cement formulations within 2 days of being spray-dried.

"Aged" polymer refers to spray dried emulsion polymer which has been placed in an oven at 60°C for 5 days prior to being incorporated into the cement formulations.

TABLE I

Materials	ME #1
Deionized water	290.00
Triton XN-45S	1.3

EP 0 731 128 A1

TABLE I (continued)

<u>Materials</u>	<u>ME#1</u>
Surfactant	35.60
Methyl Methacrylate	294.00
Allyl Methacrylate	5.60
Methacrylic Acid	75.00
Methyl 3-mercaptopropionate	13.1

TABLE II

0.1 percent aqueous solution of $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$	10.0g
14.9 percent aqueous solution of t-butyl hydroperoxide	25.4g
7.8 percent aqueous solution of sodium sulfoxylate formaldehyde	43.4g

TABLE III

deionized water	110.0g
50 percent aqueous solution of sodium hydroxide	35.0g
$\text{Ca}(\text{OH})_2$	16.1g

TABLE IV

<u>Materials</u>	<u>ME#2</u>
Deionized water	326.00 grams
Surfactant	11.30 grams
sodium lauryl sulfate	10.80 grams
Butyl Acrylate	762.00 grams
Methyl Methacrylate	739.00 grams

TABLE V

Example	Surfactant	HLB
1	Octylphenoxy ethoxylated alcohol (1-2 EO units)	3.6
2	tetramethyl decynediol	4.0
3	Ethoxylated tetramethyl decynediol	4.0
4	C12-13 linear primary alcohol ethoxylate	3.7
5	polyglycol monolaurate	3.2
Comparative 6	Octylphenoxy ethoxylated alcohol (~16 EO units)	15.8
Comparative 7	C 11-15 secondary alcohol ethoxylate	8.0
Comparative 8	C 12-13 linear primary alcohol ethoxylate	7.9
Comparative 9	Block copolymers of EO/PO	1-7
Comparative 10	Block copolymers of EO/PO	12-18

EP 0 731 128 A1

TABLE VI

Type I Portland cement	15.0 grams
60 mesh sand	22.5 grams
Spray dried emulsion polymer	1.0 grams (based on polymer solids)
water	6.0 grams

TABLE VII

Example	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>Comp.</u> <u>6</u>	<u>Comp.</u> <u>7</u>	<u>Comp.</u> <u>8</u>	<u>Comp.</u> <u>9</u>	<u>Comp.</u> <u>10</u>
HLB	3.6	4.0	4.0	3.7	3.2	15.8	8.0	7.9	1-7	12-18
Particle size (nm)	172	161	149	161	158	156	164	150	161	161
Scrap Ratio	25.0	27.3	24.0	13.8	19.3	10.4	10.9	10.0	16.1	8.8
Wet-out time (sec.)	20	15	15	15	20	25	15	15	20	15
Thin Section Toughness										
Fresh	good	very good	very good	good	very good	poor	fair	fair	fair	poor
Aged	good/fair	good	good/fair	fair/poor	fair	very poor	poor	poor	good fair	very poor
Thin Section Adhesion										
Fresh	good	very good	very good	good	good	fair	good	good	very good	fair
Aged	good	good	good	fair	fair-good	very poor	poor	poor	good	very poor

The data in Table VII show, for example, that spray-dried polymer powders prepared from emulsions containing emulsion polymers and low HLB nonionic surfactants, namely alkylphenoxy ethoxylates, acetylenic polyols, or alkylene glycol alkylates, exhibit an improved balance of properties with regard to scrap ratio and stability.

Claims

1. A method comprising

(i) providing an emulsion comprising at least one emulsion polymer and at least one surfactant having an HLB

value below 7 wherein said surfactant is a nonionic surfactant selected from the group consisting of alkylphenoxy ethoxylates, acetylenic polyols, alkylene glycol alkylates, sorbitan alkalates, glycerol esters, polyglycerol esters, and combinations thereof; and

(ii) spray-drying the emulsion.

2. The method of claim 1, wherein the at least one surfactant has an HLB value below 6.

3. The method of claim 1, wherein the at least one surfactant has an HLB value below 5.

4. The method of claim 1, wherein the nonionic surfactant is selected from the group consisting of octylphenoxy ethoxylated alcohols, ethoxylated tetramethyl decynediol, propylene glycol monolaurate, sorbitan monostearate, sorbitan oleate, glycerol oleate, decaglycerol decastearate, decaglycerol decaoleate, and combinations thereof

5. The method of claim 1, wherein the at least one surfactant is present at a level of from 0.5 to 15 percent by weight based on the total weight of said emulsion polymer.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 30 0936

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	EP-A-0 239 084 (S.C. JOHNSON & SON, INC.) * claims 1,5,7 * * page 3, line 20-21 * * page 3, line 32-49 * * page 4, line 5-12 * * example 1 * * page 17, line 36 * ---	1-5	C08J3/12 //C04B24/26
X	US-A-4 203 879 (R.C. DEWALD ET AL.) * claim 1 * * column 4, line 3-41 * ---	1-5	
X	GB-A-1 525 864 (STAUFFER CHEMICAL COMPANY) * claims 1,7,8 * * page 2, line 70-95 * ---	1-5	
D,A	EP-A-0 522 791 (ROHM AND HAAS COMPANY) * claim 1 * -----	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			C08J
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 6 May 1996	Examiner Hallemesch, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 (3.11.94) (P&C/01)